

Description

INOFLON™ 620 is a white powder (see Table I) with a nominal particle size of 65 μm . The unique characteristics of this fine cut resin include its relatively low bulk density and low shrinkage. It has high tensile strength and elongation values.

INOFLON™ 620 is ideal for general purpose mouldings such as billets and sheets, where a balance between parts economics and mechanical and electrical properties are required. A somewhat lower bulk density of INOFLON™ 620 may limit the size of mouldings from a given mould or press opening (daylight). When correctly processed, products fabricated from INOFLON™ 620 exhibits the superior properties at service temperatures in the range of -240°C to (-400°F) to $+260^{\circ}\text{C}$ ($+500^{\circ}\text{F}$) such as chemical inertness to almost every industrial chemical and solvent, low friction and non-stick surfaces along with high tensile strength and elongation value. Moulded articles are moderately stiff possess tensile properties that meet requirements of many applications.

Parts made from INOFLON™ 620 resist ignition when exposed to fire and do not spread flame. These parts generate a small amount of heat and smoke when ignited by an external flame source. These remarks are not intended to predict the hazards of burning of PTFE in an actual fire.

Typical End Use Products

Many end products are fabricated by moulding INOFLON™ 620 and machining of shapes. Examples include skived sheets and films, gaskets, seals, bridge or pipeline bearing pads, piston rings etc.

FDA Compliance

When products made from INOFLON™ 620 are correctly processed, that is sintered at high temperatures as practiced by the industry; they may comply with FDA Regulation 21 CFR 177.1550 for use in contact with food.



For more information, please contact Gujarat Fluorochemicals Limited at:

Corporate & Marketing Office:

INOX Towers, Plot No.17, Sector 16A
Noida- 201301, U.P., INDIA
Tel: +91 - 120 - 306 3600
Fax: +91 - 120 - 306 3610

Works:

12/A, GIDC Dahej Industrial Estate, Tehsil Vagra,
Distt. Bharuch - 392130, Gujarat, INDIA
Website: www.gfl.co.in
Email: inoflon@gfl.co.in

Before using, the powder must be conditioned above 19°C (66°F). First the mould is filled manually with the resin. Next, it is compacted into a preform that has a shape similar to the final shape of the desired moulding. The preform is then sintered in an oven where it undergoes heating and cooling cycles, in which heating and cooling rates and dwell times are defined and programmed. The two cycles together are commonly called *sintering cycle*. The preform is heated to a temperature above the crystalline melting point of the resin during the *sintering cycle*. The cooling cycle is used to control the crystallinity of the part. The properties of a part are functions of preforming pressure, dwell time, sintering time and temperature and the cooling rate.

Table I - Typical Properties of INOFLON™ 620

Properties	Test Method	Unit	Nominal Value
Bulk Density	ASTM D 4894	g/l	375
Avg. Particle Size	ASTM D 4894	µm	65
Mould Shrinkage (max.)	ASTM D 4894	%	3
Std. Specific Gravity	ASTM D 4894	-	2.16 - 2.18
Melting Point Initial	ASTM D 4894	°C (°F)	342 (648)
Melting Point Second		°C (°F)	327 (621)
Tensile Strength (min.)	ASTM D 4894	Mpa (Psi)	27 (3900)
Elongation (min.)	ASTM D 4894	%	280

Note: These are typical properties and are not to be used for specification purposes.

Safety Precautions

Handling and processing of PTFE must be done in ventilated areas to prevent personnel exposure to the fumes liberated during sintering and heating of the resin. Fumes should not be inhaled and eye and skin contact must be avoided. In case of skin contact, wash with soap & water immediately. In case of eye contact, flush with water immediately and seek medical help. Smoking tobacco or cigarettes contaminated with PTFE may result in a flu-like condition including chills, fever and sore throat that may not occur until a few hours after exposure has taken place. This symptom usually passes within about 24 hours. Vapors and gases generated by PTFE during sintering must be completely removed from the factory areas. Mixtures of some metal powders such as magnesium or aluminum are flammable and explosive under some conditions. Please read the Material Safety Data Sheet and the detailed information in the "Guide to the Safe Handling of Fluoropolymer Resins" published by the Fluoropolymer Division of The Society of the Plastics Industry available at www.fluoropolymers.org.

Handling and Storage

Preforming at temperatures in the range of 23-28°C (73-82°F) is most preferable. Resin temperature must be above 19°C (66°F) during moulding because of a special molecular transition of PTFE at 19°C (66°F). PTFE molecule, which has a helical shape, tightens up by transition from a helix where 15 carbons are required for 180° turn to 13 carbons. Below 19°C (66°F), PTFE molecule becomes stiff and less conformable, thus there is a chance that moulded parts could end up cracked. PTFE powder becomes sticky, forms lumps and loses all flow at temperatures above 28°C (82°F).

For best results, the powder processing areas should be kept clean and free of all contamination. Organic contamination and foreign matter usually appear as dark spots often easily visible against the white PTFE background. Organic contamination material degrades at the sintering temperatures and forms discolored spots. They oxidize away as carbon dioxide wherever sufficient oxygen exposure takes place. It is, therefore, not unusual to encounter discoloration inside a part away from the surface where hardly any oxygen is present.

Packaging

INOFLON™ 620 is packed in plastic or fiber drums or corrugated boxes. Inside of this, resin is filled in double liner bags & closed with a plastic tie.

INOFLON™ is the Trademark of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoropolymer resins. INOFLON™ can only be used in applications duly approved by GFL. Customers who may plan to use the word INOFLON™ as a trademark on or relation to their own fluoropolymer parts and other products in any style or combination or in any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL's fluoropolymer resins is permitted to claim that their products contain INOFLON™ without prior permission from GFL.

The information provided in the bulletin is furnished at no cost to the recipient and is based on information and technical data that Gujarat Fluorochemicals Limited (GFL) believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and insure that their specific conditions of processing, present no health or safety hazards. GFL does not warrant, either expressly or impliedly, in respect of use of this information for application of its INOFLON™ branded fluoropolymer resins and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as grant of license by GFL to operate under or a recommendation to infringe any patents.

NOTE Warning: Do not use any of INOFLON™ PTFE resins in medical devices that are designed for permanent implantation in the human body. For other medical uses, prior permission of GFL may be sought.