

Description

INOFLON[®] M 690 is a white powder with nominal particle size of 25 µm. This next generation fine cut resin is chemically modified to give superior performance than standard PTFE. This new material offer engineering products with higher permeation resistance, lower creep, longer flex life, smoother surfaces with higher transparency and better high-voltage dielectric properties and weldability with higher mechanical properties. Modified PTFE has the same performance characteristics of standard PTFE, viz. exceptional chemical resistance, high and low temperature capabilities, anti-stick performance and low friction.

Its significantly lower melt viscosity than standard PTFE gives better particle fusion during sintering and smoother surfaces results improved performance. Manufacturing components of INOFLON[®] M 690 is easier and more efficient than ever before, due to the high-strength welding and thermoforming capabilities. Parts and shapes made of modified PTFE can be assembled by heat welding and shaped by thermoforming. They can be joined without adhesives using moderate pressure in an oven, developing bonds with strength approaching that of the parts themselves. Welded sections can be subsequently thermoformed with no significant loss of strength.

Typical End Use Products

INOFLON[®] M 690 is a fine-cut resin designed for compression molding of blocks and sheets and for use as a base resin for compounds. Due to its significantly reduced cold flow properties, it can be used preferably in application such as seal rings, valve seats or bearing pads. The usage as compounds makes this reduced cold flow benefit even more beneficial.

The improved barrier properties, a consequence of the reduced permeation, makes the material to be the ideal solution for diaphragms, bellows, pressure house bearings, linings and encapsulations.

FDA Compliance

When products made from INOFLON[®] M 690 are correctly processed, that is sintered at high temperature practiced by industries; they may comply with FDA Regulation 21 CFR 177.1550 for use in contact with food.

Processing

Before using, the powder must be conditioned above 19°C (66.2°F). First mold is filled with resin and compacted into preform that is similar to final shape of desired molding. Preforming is easiest when the resin temperature is uniform between 21-27°C (69.8-80.6°F). As temperature declines below this range, the resin will be increasingly difficult to mold without cracks due to problem of condense moisture.

For more information, please contact Gujarat Fluorochemicals Limited at:

Corporate & Marketing Office :

INOX Towers, Plot No.17, Sector 16A
Noida-201301, U.P., INDIA
Tel : +91-120-6149600
Fax : +91-120-6149610

Works :

12/A, GIDC Dahej Industrial Estate, Tehsil Varga
Distt. Bharuch-392130, Gujarat, INDIA
Website : www.gfl.co.in
Email : inoflon@gfl.co.in



Typical Properties of INOFLON® M 690

The preform is then sintered in an oven where it undergoes controlled heating and cooling cycle. The two cycles together are commonly called sintering cycle and peak holding temperature is called sintering temperature. The sintering temperature should be in the range of 370-375 °C (698-707 °F).

Safety Precautions

Handling and processing of PTFE must be done in ventilated area to prevent personnel exposure to the fumes liberated during sintering and heating of the resin. Fumes should not be inhaled, eye and skin contact must be avoided.

In case of skin contact wash with soap and water. In case of eye contact flush with water immediately and seek medical help. Smoking tobacco or cigarettes contaminated with PTFE may result in a flu-like condition including chills, fever and sore throat that may not occur for a few hours after exposure has taken place. This symptom usually passes within about 24 hours. Vapors and gases generated by PTFE during sintering must be completely removed from the factory areas. Mixtures of some metal powders such as magnesium or aluminum are flammable and explosive under some conditions. Please read the Material Safety Data Sheet and the detailed information in the "Guide to the safe handling of Fluoropolymers Resins" published by the fluoropolymer division of the Society of the Plastics Industry available at www.fluoropolymers.org

Handling and Storage

INOFLON® M 690 is being produced in a clean environment and therefore the ideal resin for all applications where superior cleanliness is required, especially such as production, storage and transportation of ultrapure chemicals for semiconductor production. Therefore for best results the powder processing areas should be kept clean and free of all contamination. Organic contamination and foreign matter usually appear as dark spots often easily visible against the translucent modified PTFE background. Organic contamination material degrades at the sintering temperatures and forms discolored spots. They oxidize away as carbon dioxide wherever sufficient oxygen exposure takes place. To avoid contamination and discoloration throughout the whole INOFLON® products, it is recommended to process the modified INOFLON® grades under special cleanliness precautions. This is required for those production areas, where the product is handled as a powder. As soon as the billet is moulded the cleanliness of the powder can be considered to be 'protected'. Storage of PTFE at 23°C (73.4°F) or lower prevents lump formation as a result of movement and transportation.

Packaging

INOFLON® M 690 is packed in plastic or fiber drums. Inside of this, resin is filled in double liner bags & closed with plastic tie.

INOFLON® is the registered trademark of Gujarat Fluorochemicals Limited (GFL) used for its brand of fluoropolymer resin. INOFLON® can only be used in applications duly approved by GFL. Customers who plan to use the word INOFLON® as a trade mark on or relation to their own fluoropolymer parts and other products in any style or combination or in any manner whatsoever must contact GFL for prior permission for such use. No consumer/user of GFL's fluoropolymer resins is permitted to claim that their products contain INOFLON® without prior permission from GFL.

Properties	Test Method	Unit	Nominal Value
Bulk density	ASTM D 4894	g/L	375
Avg. Particle Size (d ₅₀)	ASTM D 4894	µm	25
Mold Shrinkage	ASTM D 4894	%	4-6
Std. Specific Gravity (SSG)	ASTM D 4894	-	2.15-2.18
Melting Point	ASTM D 4894	°C (°F)	342 (648) 327(621)
Tensile Strength	ASTM D 4894	MPa(Psi)	35 (5076)
Elongation	ASTM D 4894	%	450

Note: These are typical properties and not to be used for specification purpose

The information provided in the bulletin is furnished at no cost to the recipient and is based on information and technical data that Gujarat Fluorochemicals Limited (GFL) believes is correct and sound. Those who choose to use the information must be technically qualified, and do so entirely at their own cost and risk. The users must determine and insure that their specific conditions of processing, present no health or safety hazards. GFL does not warranty, either expressly or impliedly, in respect of use of this information for application of its INOFLON® branded Fluoropolymer resins and shall bear no liability as a result of any loss or damage caused directly or indirectly due to use of any information provided in this bulletin. Nothing contained herein can be taken or construed as grant of license by GFL to operate under or a recommendation to infringe any patents.

NOTE Warning : Do not use any of INOFLON® PTFE resins in medical devices that are designed for permanent implantation in the human body. For other medical uses, prior permission of GFL may be sought.