

FLUORSPAR (CaCl₂)



TECHNICAL DATA SHEET

Parameters	Unit	Value
CaF ₂	% min.	97.0
SiO ₂	% max.	1.0
CaCO ₃	% max.	1.8
P ₂ O ₅	% max.	0.03
Sulphur as S	% max.	0.03
Magnesium	% max.	0.08
BaSO ₄	% max.	0.5
Fe	% max.	0.15
Arsenic	% max.	0.006
Mixed Oxide	% max.	1.3
Organics	% max.	0.04 - 0.06
Average Moisture	% max.	10
Cl	% max.	0.007

The above information is believed to be correct as per our analysis and research but does not purport to be all inclusive and shall be used only as a guide. The information is based on the present state of our knowledge and applies to the product concerning appropriate safety precautions. It does not represent any guarantee of the properties of the product. Gujarat Fluorochemicals shall not be held liable for any damage resulting from handling or contact with the above product.

SALES AND TECHNICAL SUPPORT

Corporate & Marketing Headquarter

INOX Towers, 17, Sector-16A,
Noida - 201301 U.P., India
+91 120 6149600

GFL GM Fluorspar SA
425, Boulevard IBN Tachefine, 3rd floor,
Casablanca, Morocco
+212 22622326

